

# MAXCIS 671-PP

## ***One Component, Polyurethane Based, Pouring System, Rubber Binder***

### **DEFINITION:**

- It is an aromatic, solvent-free prepolymer.
- It is used to bond SBR and EPDM granules in the pouring system.
- It has high adhesion strength.
- It has a flexible structure.
- It is UV resistant.
- It is resistant to outdoor conditions.

### **USAGE AREAS:**

- Pouring system SBR and EPDM rubber floor applications



### **AMOUNT OF USAGE:**

- SBR or EPDM Granules: %80-85, Binder: %15-20

### **TECHNICAL SPECIFICATIONS:**

Test Name	Unit	Value
Chemical Structure	-	Polyurethane Prepolymer
Density (25 °C)	g/cm <sup>3</sup>	1,10 ± 0,05
Viscosity (25 °C)	mPa.s	1500-2000
NCO Content	%	12,00 ± 0,50

### **PACKAGING:**

- 220 kg/drum

### **SELF LIFE AND STORAGE:**

- It should be stored in original, unopened and undamaged packages, in dry environments between 15°C-25°C, away from direct sunlight. Shelf life is 9 months.

### **WARNING:**

- Before using the product, read the MSDS form carefully and follow the written instructions.
- Personal protective equipment should be used during application.
- There must be sufficient air circulation in the application area.
- Give empty packages to organizations authorized to collect hazardous waste.